



DOWEX MARATHON MSC

A Uniform Particle Size, High Capacity Macroporous Cation Exchange Resin for Water Demineralization Applications

Product	Type	Matrix	Functional group
DOWEX [®] MARATHON [®] MSC	Strong acid cation	Styrene-DVB, macroporous	Sulfonic acid

Guaranteed Sales Specifications		Na ⁺ form	H ⁺ form
Total exchange capacity, min.	eq/l	1.7	1.6
	kg/ft ³ as CaCO ₃	37.1	35.0
Water content	%	44 - 50	50 - 56
Uniformity coefficient, max.		1.1	1.1

Typical Physical and Chemical Properties		Na ⁺ form	H ⁺ form
Mean particle size [†]	μm	500 ± 50	520 ± 50
Whole beads	%	95 - 100	95 - 100
Total swelling (Na ⁺ → H ⁺)	%	4	4
Particle density	g/ml	1.28	1.20
Shipping weight	g/l	800	760
	lbs/ft ³	50	47

Recommended Operating Conditions	• Maximum operating temperature	150°C (300°F)
	• pH range	0 - 14
	• Bed depth, min.	800 mm (2.6 ft)
	• Flow rates:	
	Service/fast rinse	5-50 m/h (2-20 gpm/ft ²)
	Backwash	see Figure 1
	Co-current regeneration/displacement rinse	1-10 m/h (0.4-4 gpm /ft ²)
• Total rinse requirement	3 - 6 Bed volumes	
• Regenerant	1-10% H ₂ SO ₄ , 4-8% HCl or 8-12% NaCl	

[†] For additional particle size information, please refer to Particle Size Distribution Cross Reference Chart (Form No. 177-01775).

Typical properties and applications

DOWEX MARATHON MSC strong acid cation resin is a highly cross-linked resin with high porosity giving excellent osmotic shock resistance and chemical and thermal stability.


The resin has a variety of uses, such as:

- Hot process softening
- Demineralization
- Adsorbent
- Processes with oxidizing conditions
- Recovery of metals from plating baths

Packaging

25 liter bags or 5 cubic feet fiber drums

Figure 1. Backwash Expansion Data




For other temperatures use:

$$F_T = F_{77°F} [1 + 0.008 (T_{°F} - 77)], \text{ where } F = \text{gpm/ft}^2$$

$$F_T = F_{25°C} [1 + 0.008 (1.8T_{°C} - 45)], \text{ where } F = \text{m/h}$$

Figure 2. Pressure Drop Data



For other temperatures use:

$$P_T = P_{20°C} / (0.026 T_{°C} + 0.48), \text{ where } P = \text{bar/m}$$

$$P_T = P_{68°F} / (0.014 T_{°F} + 0.05), \text{ where } P = \text{psi/ft}$$

DOWEX Ion Exchange Resins

For more information about DOWEX resins, call the Dow Liquid Separations business:

North America: 1-800-447-4369
 Latin America: (+55) 11-5188-9222
 Europe: (+32) 3-450-2240
 Pacific (ex. China): +800-7776-7776
 China: +10-800-600-0015
<http://www.dowex.com>

Warning: Oxidizing agents such as nitric acid attack organic ion exchange resins under certain conditions. This could lead to anything from slight resin degradation to a violent exothermic reaction (explosion). Before using strong oxidizing agents, consult sources knowledgeable in handling such materials.

Notice: No freedom from any patent owned by Seller or others is to be inferred. Because use conditions and applicable laws may differ from one location to another and may change with time, Customer is responsible for determining whether products and the information in this document are appropriate for Customer's use and for ensuring that Customer's workplace and disposal practices are in compliance with applicable laws and other governmental enactments. Seller assumes no obligation or liability for the information in this document. NO WARRANTIES ARE GIVEN; ALL IMPLIED WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE ARE EXPRESSLY EXCLUDED.

