



TULSION®

MB-115

TULSION® MB-115 is a mixture of strong acid cation exchange resin TULSION T-46 (H) and strong base anion exchange resin TULSION A-33(OH) in 1:1.5 volumetric ratio.

TULSION® MB-115 is a specially designed as a polisher to obtain low conductivity water.

TYPICAL CHARACTERISTICS

	TULSION® T-46	TULSION® A-33
Type	Strong acid cation exchange resin	Strong base anion exchange resin
Matrix Structure	Cross linked polystyrene	Cross linked polystyrene
Functional Group	Sulfonic acid	Quaternary ammonium Type I
Physical Form	Moist spherical beads	Moist spherical beads
Ionic form supplied	Hydrogen	Hydroxide
Screen Size U.S.mesh(wet)	16 to 50	16 to 50
Particle Size	0.3 to 1.2 mm	0.3 to 1.2 mm
Fines Content	Less than 0.5% passing through 50 U.S.mesh	Less than 0.5% passing through 50 U.S.mesh
Total exchange capacity	1.8 meq/ml minimum of 99% in hydrogen form	1.0 meq/ml minimum of 90% in hydroxide form and less than 1% in chloride form
pH range	0 to 14	0 to 14
Temperature stability	120°C	80°C
Solubility	Insoluble in all common solvents	Insoluble in all common solvents
Organic leachables	Less than 0.2 mg KMNO ₄ per ml of wet resin	Less than 0.2 mg KMNO ₄ per ml of wet resin
Backwash settled density		Approx. 750 gm/liter
Impurities	Fe=50 ppm(max) Cu=50 ppm(max) Pb=50 ppm(max)	Fe=50 ppm(max) Cu=50 ppm(max) Pb=50 ppm(max)
Bead strength	Avg. not less than 500g/bead by Chatillon test	Avg. not less than 300g/bead by Chatillon test

Packing

TULSION® exchange resins are available in standard packaging as follows

Steel/fibre drum with double polyethylene lined	7 ft ³ , 180 liters
Polyethylene lined HDPE bags	1 ft ³ , 25 liters

Data included herein are based on test information obtained by Thermax Limited. This data is believed to be reliable but does not imply any warranty or performance guarantee. We recommend the user determine performance by testing on his own processing equipment. We assume no liability or responsibility for patent infringement resulting from the use of the product.



THERMAX

THERMAX LIMITED

CHEMICAL DIVISION

An ISO 9001 Company

97/E, GENERAL BLOCK BHOSARI INDUSTRIAL AREA,

PUNE 411 026, INDIA

TEL: 0091-20-27120169/27120181 FAX:0091-20-27120206

EMAIL: gsatpute@thermaxindia.com

Also visit us at: <http://www.thermaxindia.com/>

In view of our constant endeavour to improve quality of our products, we reserve the right to alter or change specifications without prior notice

TCD/RES/MB-115/6-2000.