



SALES SPECIFICATION SHEET

CENTAUR NDS 12x40

Granular Activated Carbon

Test	Specification		Calgon Carbon Test Method
	Min	Max	
IODINE NO., mg/g	900	-	TM-4 or ASTM D 4607
ABRASION NO.	75	-	TM-9
ACID SOLUBLE IRON, wt%	-	0.01	TM-18
EXTRACTABLE pH	5	8	TM-15 or ASTM D 3838
MOISTURE, wt%, as packed	-	3	TM-1 or ASTM D 2867
US SIEVE SERIES			TM-8
	+12	- 5.0	
	-40	- 4.0	

This product is Made to Order

Calgon Carbon Corporation's activated carbon products are continuously being improved and changes may have taken place since this publication went to press. (1650-04/24/98)