



DOWEX MONOSPHERE MP-525C (H)

A Uniform Particle Size Macroporous Strong Acid Cation Exchange Resin for Mixed Bed Demineralization and Condensate Polishing Applications

Product	Type	Matrix	Functional group
DOWEX* MONOSPHERE* MP-525C (H)	Strong acid cation	Styrene-DVB macroporous	Sulfonic acid

Guaranteed Sales Specifications			H ⁺ form	
Total exchange capacity, min.		eq/l kgr/ft ³ as CaCO ₃	1.6 35.0	
Water content		%	50 – 54	
Bead size distribution†				
Mean particle size		μm	500 ± 50	
Uniformity coefficient, max.			1.1	
<300μ, max.		%	1	
Whole beads, min.		%	95	
Crush strength				
Average, min.		g/bead	350	
> 200 g/bead, min.		%	95	
Trace metals, ppm dry resin, max.				
Na	Fe	Cu	Al	Heavy metals (as Pb)
100	50	50	50	20

Typical Physical and Chemical Properties			
Total swelling (Na ⁺ → H ⁺)		%	4
Particle density		g/ml	1.18
Shipping weight		g/l lbs/ft ³	760 47

Recommended Operating Conditions

- Maximum operating temperature 150°C (300°F)
- pH range 0-14
- Bed depth, min. 450 mm (1.5 ft)
- Flow rates:
 - Service/fast rinse 5-50 m/h (2-20 gpm/ft²)
 - Service/condensate polishing 40-150 m/h (16-60 gpm/ft²)
 - Backwash See figure 1
 - Co-current regeneration/displacement rinse 1-10 m/h (0.4-4 gpm /ft²)
- Total rinse requirement 3 – 6 Bed volumes
- Regenerant 1-10% H₂SO₄, 4-8% HCl

† For additional particle size information, please refer to Particle Size Distribution Cross Reference Chart (Form No. 177-01775).


Typical properties and applications

DOWEX MONOSPHERE MP-525C (H) strong acid cation exchange resin is a condensate grade macroporous resin with uniform particle size, exceptional physical stability and resistance to osmotic shock. This resin is specially sized to give excellent separation after backwash when used in conjunction with DOWEX MONOSPHERE MP-725A (OH) anion exchange resin in mixed beds. In addition, the smaller bead size of DOWEX MONOSPHERE MP-525C (H) is intended to improve insoluble iron removal and reduce the regeneration and rinse water requirements compared to larger conventional type macroporous resins.

Packaging

25 liter bags or 5 cubic feet fiber drums

Figure 1. Backwash Expansion Data




For other temperatures use:

$$F_T = F_{77°F} [1 + 0.008 (T_{°F} - 77)], \text{ where } F = \text{gpm/ft}^2$$

$$F_T = F_{25°C} [1 + 0.008 (1.8T_{°C} - 45)], \text{ where } F = \text{m/h}$$

Figure 2. Pressure Drop Data



For other temperatures use:

$$P_T = P_{20°C} / (0.026 T_{°C} + 0.48), \text{ where } P = \text{bar/m}$$

$$P_T = P_{68°F} / (0.014 T_{°F} + 0.05), \text{ where } P = \text{psi/ft}$$

DOWEX Ion Exchange Resins

For more information about DOWEX resins, call the Dow Liquid Separations business:

North America: 1-800-447-4369
 Latin America: (+55) 11-5188-9277
 Europe: (+32) 3-450-2240
 Japan: (+81) 3-5460-2100
 Australia: (+61) 3-9226-3545
<http://www.dowex.com>

Warning: Oxidizing agents such as nitric acid attack organic ion exchange resins under certain conditions. This could lead to anything from slight resin degradation to a violent exothermic reaction (explosion). Before using strong oxidizing agents, consult sources knowledgeable in handling such materials.

Notice: No freedom from any patent owned by Seller or others is to be inferred. Because use conditions and applicable laws may differ from one location to another and may change with time, Customer is responsible for determining whether products and the information in this document are appropriate for Customer's use and for ensuring that Customer's workplace and disposal practices are in compliance with applicable laws and other governmental enactments. Seller assumes no obligation or liability for the information in this document. NO WARRANTIES ARE GIVEN; ALL IMPLIED WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE ARE EXPRESSLY EXCLUDED.

