



DOWEX MSA-1 C

A Macroporous Strong Base Anion Exchange Resin for Mixed Bed Demineralization Applications

Product	Type	Matrix	Functional group
DOWEX* MSA-1 C	Type 1 strong base anion	Styrene-DVB, macroporous	Quaternary amine

Guaranteed Sales Specifications		Cl ⁻ form
Total exchange capacity, min.	eq/l	1.0
	kgr/ft ³ as CaCO ₃	21.9
Water content	%	56 - 64
Bead size distribution†		
>1.4 mm, max. (14 mesh)	%	0
>1.2 mm, max. (16 mesh)	%	2
<0.42 mm, max. (40 mesh)	%	2
Whole beads, min.	%	95

Typical Physical and Chemical Properties		Cl ⁻ form
Total swelling (Cl ⁻ → OH ⁻)	%	15
Particle density	g/ml	1.06
Shipping weight	g/l	670
	lbs/ft ³	42

Recommended Operating Conditions	• Maximum operating temperature	100°C (212°F)
	• pH range	0-14
	• Bed depth, min.	450 mm (1.5 ft)
	• Flow rates:	
	Service/fast rinse	5-50 m/h (2-20 gpm/ft ²)
	Service/condensate polishing	40-150 m/h (16-60 gpm/ft ²)
	Backwash	See Figure 1
• Total rinse requirement	3-6 Bed volumes	
• Regenerant:		
Type	4-8% NaOH	
Temperature	Ambient or up to 50°C (122°F)	
		for silica removal

† For additional particle size information, please refer to Particle Size Distribution Cross Reference Chart (Form No. 177-01775).


Typical properties and applications

DOWEX MSA-1 C strong base anion exchange resin is a condensate grade macroporous resin with exceptional physical stability and resistance to osmotic shock.

Packaging

25 liter bags or 5 cubic feet fiber drums

Figure 1. Backwash Expansion Data




For other temperatures use:

$$F_T = F_{77°F} [1 + 0.008 (T_{°F} - 77)], \text{ where } F \equiv \text{gpm/ft}^2$$

$$F_T = F_{25°C} [1 + 0.008 (1.8T_{°C} - 45)], \text{ where } F \equiv \text{m/h}$$

Figure 2. Pressure Drop Data



For other temperatures use:

$$P_T = P_{20°C} / (0.026 T_{°C} + 0.48), \text{ where } P = \text{bar/m}$$

$$P_T = P_{68°F} / (0.014 T_{°F} + 0.05), \text{ where } P = \text{psi/ft}$$

DOWEX Ion Exchange Resins
For more information about DOWEX resins, call the Dow Liquid Separations business:

North America: 1-800-447-4369
 Latin America: (+55) 11-5188-9222
 Europe: (+32) 3-450-2240
 Pacific (ex. China): +800-7776-7776
 China: +10-800-600-0015
<http://www.dowex.com>

Warning: Oxidizing agents such as nitric acid attack organic ion exchange resins under certain conditions. This could lead to anything from slight resin degradation to a violent exothermic reaction (explosion). Before using strong oxidizing agents, consult sources knowledgeable in handling such materials.

Notice: No freedom from any patent owned by Seller or others is to be inferred. Because use conditions and applicable laws may differ from one location to another and may change with time, Customer is responsible for determining whether products and the information in this document are appropriate for Customer's use and for ensuring that Customer's workplace and disposal practices are in compliance with applicable laws and other governmental enactments. Seller assumes no obligation or liability for the information in this document. NO WARRANTIES ARE GIVEN; ALL IMPLIED WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE ARE EXPRESSLY EXCLUDED.

